

Case Study: Commercial

University of Waterloo

Industry: Education Location: Waterloo, Ontario, Canada Architect: Kuwabara Payne McKenna Blumberg Architects

University of Waterloo used Plyboo plywood veneer and flooring extensively throughout the school. Applications included Havana strand and edge grain amber plywood for wall systems. A first on this project was the use of Havana strand veneers in the construction of over 300 doors in this contemporary space. Havana strand flooring and custom stair treads featured prominently

Possible LEED Credits: Low emitting materials and certified wood Floorscore Certified



Materials Used:



Amber Edge Grain Plywood BP-V4896A-NAUF/FSC

Havana Strand Plywood and Flooring



Havana Strand Veneer BP-24898PD-NAUF/FSC

FL-P5872PD-NAUF/FSC

SMITH & FONG.

Physical / Mechanical Properties - Strand Bamboo Veneer

Dimensions:	3/4" x 48" x 96"
	19mm x 1219mm x 2438mm (*mm tolerance +/5mm thickness)
Construction:	Three-ply, cross core construction.
Working with Plyboo:	A worksheet is provided with each panel containing useful tips and infor- mation and is also available on our website at plyboo.com/downloads.
ASTM E84: Surface Burning	Class C
ASTM D1037: Dimensional Stability	 Linear Expansion (3-ply): Parallel -0.09% / Perpendicular -0.07% Thickness Swell (3-ply): -0.3%
	Screw Hold (3-ply) (face/back/edge) • 1009lbs/ 681 lbs/ 516 lbs average
ASTM D4442: Moisture Content	6-9% average
ASTM D 6007-02: Formaldehyde Concen- tration in Air from Wood Products, small chamber test	Plyboo = 0.004 ppm (surpasses CARB II standards, 0.05ppm & ULEF standards of 0.04ppm)

Physical / Mechanical Properties - Edge Grain Bamboo Plywood

Dimensions:	3/4" x 48" x 96" 19mm x 1219mm x 2438mm (*mm tolerance +/5mm thickness)
Construction:	Three-ply, cross core construction.
Working with Plyboo:	A worksheet is provided with each panel containing useful tips and infor- mation and is also available on our website at plyboo.com/downloads.
ASTM E84: Surface Burning	Class C
ASTM D1037: Dimensional Stability	 Linear Expansion (3-ply): Parallel -0.04% / Perpendicular -0.07% Thickness Swell (3-ply): -0.13% Screw Hold (3-ply) (face/back/edge) 742 lbs/ 831 lbs/ 860 lbs average
ASTM D4442: Moisture Content	6-9% average
ASTM D 6007-02: Formaldehyde Concen- tration in Air from Wood Products, small chamber test	Plyboo = 0.004 ppm (surpasses CARB II standards, 0.05ppm & ULEF standards of 0.04ppm)

Physical / Mechanical Properties - Strand Bamboo Flooring

Dimensions:	9/16" x 3 3/4" x 72" - 14mm x 96mm x 1830mm
Installation:	Tongue and Groove, glue down
ASTM E648:Critical Radiant Flux:	Class 1
ASTM D1037: Dimensional Stability	Linear Expansion: Parallel -0.02%, Perpendicular -0.23%, Thickness Swell -0.25%, Hardness (Janka Ball Test): 3,500 lbf average
ASTM D2394: Coefficient of Friction	Static Coefficient/Dynamic (Sliding) Coefficient: 0.562/ 0.497
ASTM 4442: Moisture Content	6-9% average
ASTM D5116: Organic Emission (CA Section 01350)	Classroom scenario/Office scenario: Pass/Pass